




# Synteon SC20K

## Woven High Strength Polyester



Synteon SC20K is composed of high molecular weight, high tenacity multifilament polyester yarns that are woven into a stable network placed under tension. Synteon SC20K is inert to biological degradation and is resistant to naturally encountered chemicals, alkalis and acids.



PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Tensile Strength	<u>ASTM D-4595</u>	20,580 lbs/ft	300.4 kN/m
Tensile Strength @ 5 % Strain	<u>ASTM D-4595</u>	8,544 lbs/ft	124.7 kN/m
(LTDS) Long Term Design Strength	GRI-GT7	10,500 lbs/ft	153.2 kN/m
Partial Factor -Environmental Effects Environment, 3 < pH < 9	GRI-GG7, GRI-GG8)	1.1 RFd	1.1 RFd
Partial Factor -Installation Damage (sand/silt/clay)	ASTM D 5818	1.18 RFid	1.18 RFid
Reduction Factor - Creep		1.51	1.51

## Synteon SC20K Shipping & Packaging Information

SIZE	WIDTH	AREA
16.4' x 300'	16.4'	546.67 y <sup>2</sup>

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
US Fabrics assumes no liability in connection with the use of this information.