




# US 330NWE

## Environmental Nonwoven Geotextile

GEOMEMBRANE  
CUSHION



NTPEP APPROVED - GTX-2019-01-208. US 330NWE is a 12 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 330NWE is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13. US 330NWE meets the following M.A.R.V. values:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	<a href="#">ASTM D-5261</a>	12 oz/y <sup>2</sup>	406.8 g/m <sup>2</sup>
Thickness <sup>(1)</sup>	<a href="#">ASTM D-5199</a>	120 mils	3.048 mm
Grab Tensile Strength	<a href="#">ASTM D-4632</a>	330 lbs	1,470 N
Elongation @ Break	<a href="#">ASTM D-4632</a>	50 %	50 %
CBR Puncture	<a href="#">ASTM D-6241</a>	900 lbs	4,005 N
Trapezoidal Tear	<a href="#">ASTM D-4533</a>	125 lbs	556 N
Apparent Opening Size <sup>(1,2)</sup>	<a href="#">ASTM D-4751</a>	100 US Sieve	0.149 mm
Permittivity <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	0.9 Sec <sup>-1</sup>	0.9 Sec <sup>-1</sup>
Permeability <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	0.3 cm/sec	0.3 cm/sec
Water Flow Rate <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	70 g/min/f <sup>2</sup>	2,852 L/min/m <sup>2</sup>
UV Resistance @ 500 Hours	<a href="#">ASTM D-4355</a>	70 %	70 %

<sup>(1)</sup> At the time of manufacturing. Handling, storage, and shipping may change these properties.

<sup>(2)</sup> Maximum average roll value (MaxARV).

## US 330NWE Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
15' x 480'	31"	15'	620 lbs	800 y <sup>2</sup>	27
15' x 300'	24"	15'	395 lbs	500 y <sup>2</sup>	80

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**

**Phone: (800) 518-2290 | Fax: (513) 271-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
US Fabrics assumes no liability in connection with the use of this information.